



MELox™ Yttria Stabilised Zirconias

MELox™ yttria stabilised zirconias are high performance, high purity zirconium oxides suitable for use in a range of demanding applications.

MELox™ stabilised zirconias are manufactured in the UK by a precisely controlled chemical precipitation process that ensures consistency of both purity and performance together with a fully homogeneous distribution of yttria.

Features

Yttria stabilised zirconium oxides with high reactivity and sintering.

Spray-dried, free-flowing powders that are easy to handle.

Outstanding performance properties for final zirconia ceramic parts.

Applications

MELox™ stabilised zirconias are commonly used, for example, in:

- 3Y – wear parts, structural ceramics and dental prostheses
- 5Y – oxygen sensors
- 8Y – solid oxide fuel cell electrolytes

Discover more at

www.luxfermeltechnologies.com

 @LuxferMELTech

† The information contained within is meant as a guideline only

Copyright © Luxfer MEL Technologies 2018. The information provided within this document is aimed to assist manufacturers and other interested parties in the use of Luxfer MEL Technologies products. Luxfer MEL Technologies accepts no liability in whole or in part from use and interpretation of the data herein. All information is given in good faith but without warranty. Freedom from patent rights must not be assumed. Health and Safety information is available for all Luxfer MEL Technologies products. **DS-1030-0219**



Certificate No. FM12677

Chemical composition (typical values)

Grade	Y ₂ O ₃ (wt%)	SiO ₂ (wt%)	Fe ₂ O ₃ (wt%)
MELox™ 3Y	5.3	0.02	0.01
MELox™ 5Y	8.0	0.02	0.01
MELox™ 8Y	13.6	0.02	0.01

Physical properties (typical values)

Grade	Sintered flexural strength (MPa)*	Sintered density (g.cm ⁻³)*	Powder particle size D ₅₀ (µm)	Powder surface area (m ² .g ⁻¹)
MELox™ 3Y	>1000	6.05	0.45	10 - 17
MELox™ 5Y	-	>5.95	0.45	10
MELox™ 8Y	-	>5.90	0.45	10

*Sintered at 1450 °C

Packaging

Standard packaging is 25 kg packed into poly-lined fibre-board drums.

Safety data sheet

Regional SDS information is available on request.