



## Elektron Cast Billet

Direct chill cast billet is manufactured by Luxfer MEL Technologies as the starting material for other magnesium products, such as sheet, forgings and extrusions. However, it has been frequently found that the cast billet is suitable for machining into prototypes, thus avoiding expensive tooling, and in some cases for production where the size of the finished item is outside economic casting or extrusion dimension or minimum economic production.

Cast billet is supplied to the compositional requirements but not the mechanical properties of the British/ASTM Standard for the corresponding wrought or cast alloy. With conventional casting alloys, if the billets were to be heat treated it would be expected that the specification minimum properties would be obtained though, due to the casting technique employed, no guarantee could be given.

Inspection standards for cast billet will be by agreement. Ultrasonic inspection to AMS-STD-2154 Class A or Class AA is available upon request. Temporary corrosion preventative surface treatments can be applied by agreement.

### Continuous cast machining stock

Luxfer MEL Technologies supplies direct chill continuous cast machining stock for manufacture of parts which are larger than possible by conventional production methods. Stock is rectangular, with two opposing faces machined, and then sawn to ordered size. The alloy for machining stock is AZ31B per the chemical composition requirements of ASTM B90.

Maximum thickness:	330 mm
Maximum width:	1115 mm
Maximum length:	2080 mm

## Nominal weight of available cast billet (kilograms per metre of billet length)

Diameter (mm)	Machined billets								As-cast billets	
	73 Ø	100 Ø	175 Ø	220 Ø	246 Ø	295 Ø	384 Ø	398 Ø	410 Ø	447 Ø
Length (mm)	25-600	25-600	25-600	25-600	25-600	25-600	25-840	500-1825	500-1825	500-1825
A8	7.5	-	-	-	-	-	-	-	-	-
AZComm	-	-	-	-	-	-	-	-	232	276
AZ21X1	-	-	-	-	-	-	-	-	232	276
AZ31B	-	-	-	-	-	-	-	-	234	278
AZ61A	-	-	-	-	-	-	207	-	236	281
AZ80A	-	-	43.3	68.4	85.6	123	-	224	-	-
AZ855	-	-	43.3	68.4	85.6	123	-	-	-	-
AZ91	7.6	-	-	-	-	-	-	-	-	-
AZM	7.5	-	-	-	-	123	-	-	-	-
M1C	-	-	-	-	-	-	-	-	231	275
MSR	7.6	-	-	-	-	-	-	-	-	-
Pure Mg	7.3	-	41.9	66.1	82.7	119	-	-	-	-
RZ5	7.7	-	-	-	-	-	-	-	-	-
WE43	7.7	14.5	44.3	69.9	87.5	-	-	-	-	-
WE54	7.7	14.5	44.5	70.3	87.9	-	-	-	-	-
ZA	7.3	-	42.1	66.5	83.2	120	-	-	-	-
ZK60A	-	-	-	-	-	-	-	226	-	-
ZRE1	7.5	-	-	-	-	-	-	-	-	-
ZW3	-	-	43.3	68.4	85.6	123	-	-	-	-

Alloy and size combinations without a listed weight may be available on inquiry.

Discover more at  
[www.luxfermeltechnologies.com](http://www.luxfermeltechnologies.com)



† The information contained within is meant as a guideline only

Copyright © Luxfer MEL Technologies 2018. The information provided within this document is aimed to assist manufacturers and other interested parties in the use of Luxfer MEL Technologies products. Luxfer MEL Technologies accepts no liability in whole or in part from use and interpretation of the data herein. All information is given in good faith but without warranty. Freedom from patent rights must not be assumed. Health and Safety information is available for all Luxfer MEL Technologies products. **DS-1013-1118**



Certificate No. FM12677

**Luxfer MEL Technologies**  
 Elektron Technology Centre  
 Lumns Lane, Manchester, M27 8LN, UK  
 T +44 (0) 161 911 1000

**Luxfer MEL Technologies**  
 500 Barbertown Point Breeze Road  
 Flemington, NJ 08822, USA  
 T +1 908 782 5800

**Luxfer MEL Technologies**  
 4601 Westown Parkway Suite 130  
 West Des Moines, IA 50266  
 T +1 515 421 4100